



COEPOX 122

抗油防潮环氧底涂 EPOXY PRIMER WITH OIL AND MOISTURE RESISTANCE

COEPOX 122 是双组份无溶剂环氧树脂涂料，可用于潮湿或油污污染的混凝土基面。环保无溶剂，具有良好的渗透性以及卓越的机械性能，用途广泛。

COEPOX 122 is a two-component, solvent-free epoxy primer for damp or oil-contaminated substrate. COEPOX 122 is environmental-friendly and solvent-free with good penetration, excellent mechanical properties and wide range of uses.

适用场所 Applications

- > 作为密封剂，封闭多孔隙的、被油污污染的混凝土基面
As sealant to seal porous, oil-contaminated concrete substrate
- > 作为密封剂，封闭多孔隙的潮湿混凝土基面
As sealant to seal porous, damp concrete substrate
- > 作为普通环氧或聚氨酯材料的黏结剂
As bonding agent for epoxy or polyurethane materials
- > 破损地面的修补及找平
Repairing and levelling of the damaged floors

无溶剂、环保型
Solvent-free, environment-friendly

抗油防潮
Oil and moisture resistance

良好的渗透性
Good penetration

卓越的机械性能
Excellent mechanical performance

多用途、易施工
Multi-function, easy to apply

技术标准 Technical standard	
固体含量 Solid content	100%
混合物比重 Density of mixture	~1.7g/cm ³
混合物粘度 Viscosity of mixture	~3700MPa·s
邵氏硬度 Shore hardness	>75
拉拔强度 Pull-off strength (油污基面 Oily surface)	>2MPa
拉拔强度 Pull-off strength (潮湿基面 Damp surface)	>2MPa



步骤 Step	产品 Product	说明 Information	理论用量 Consumption	施工方法 Application method	覆涂间隔时间 Overcoating
基面 Substrate	处理 Preparation	机械处理，清洁 Mechanical treatment and cleaning of base	/	/	/
底涂 Primer	COEPOX 122	抗油防潮环氧底涂 Epoxy primer with oil and moisture resistance	0.6~1.0kg/m ²	滚涂/刮涂 Roller/Scraper	
撒播 Broadcast	石英砂 QUARTZ 0.6~1.2	在刚施工好的底涂上播撒少量石英砂 Broadcast of quartz on freshly-applied primer	1.5~2.0kg/m ²	用手播撒 Scatter by hand	8小时后 Allow 8 hours
后续涂层 Next coats	科兰其他产品 COELAN Products	COELAN推荐的地坪系统 Flooring systems recommended by COELAN	/	/	/

